

*Denomination:* **1/2 VITELLO SNK**

Documento Rev. del Date of document Pag./di  
MOD030 - STP 02 01/09/2012 23/03/2021 1/2

## Identification

*Destination:* Footwear  
*General informations:* Smooth half calf

## Characteristics

<i>Raw material</i>	Calf (Bos Taurus)
<i>Tannage mode</i>	Chrome
<i>Dyeing mode</i>	In drum not passing
<i>Colour Uniformity</i>	As sample
<i>Finishing mode</i>	Pigmented
<i>Realized colors</i>	As per color card
<i>Grain aspect</i>	Smooth
<i>Elasticity, Grain-tightening, Softening, Fullness</i>	As sample
<i>Size (sqm)</i>	1,20 - 1,57
<i>Thickness (mm)</i>	1,1 - 1,2

## Technical value

<i>Ball burst test - Elongation at break</i>	≥ 7,00	mm
<i>Flexing endurance - chromatic Variation</i>	dopo 40000 cicli a secco ≥ 3	I.G.S. degree
<i>Flexing endurance - Break of grain</i>	dopo 40000 cicli a secco ≥ No break	Judgment
<i>Flexing endurance - chromatic Variation</i>	dopo 10000 a umido ≥ 3	I.G.S. degree
<i>Flexing endurance - Break of grain</i>	dopo 10000 a umido = No break	Judgment
<i>Colour resistance to light - chromatic Variation</i>	dopo 72 h ≥ 3/4	I.B.S.degree

### **Compliance declarations**

The product is identified in section 4.1.1 of the EN 15987:2015 standard and it is made in compliance with the following standards and regulations:

- Washington Convention dated 03/03/1973 validated with the Law 19/12/1975 n. 874 and adopted with the Regulation n. EC 388/97 on the protection of species of wild flora and fauna through the control of their trade;

- Regulation n. EC 1907/2006 (REACH): Annex XIV and Annex XVII;

- Directive n. 93/42/EEC on medical devices adopted with the Legislative Decree n. 46 dated 24/02/1997;

- Chemical characteristics of acceptability provided for by UNI 10594 and UNI 10826;

**IMPORTANT NOTICE:** The product compliance with the eco-toxicological requirements, provided for by the above mentioned Regulation n. EC 1907/2006, is guaranteed for the skins as they are sold from the tannery. There where the buyer should apply any further chemical treatments on the skins, in order to ensure the sold from the tannery. There where the buyer should apply make sure of the compliance of the applied substances with the cited regulation and that they do not negatively interact with the on sure of the compliance of the applied substances. Casandrina tannery will not be legally liable for the loss of compliance of its products.

## Note



Quality Management System  
(UNI EN ISO 9001:2008)



Environmental Management System  
(UNI EN ISO 14001:2004)



Leather from Italy  
(UNI 11239:2007)



UNIC Social Accountability  
(In accordance with SA8000)



Health and Safety  
(OHSAS18001)

## Product technical reference

Denomination: **1/2 VITELLO SNK**

Documento	Rev.	del	Date of document	Pag./di
MOD030 - STP	02	01/09/2012	<b>23/03/2021</b>	2/2

### Usage Indications

The skin is a natural product. Therefore, in order to use it correctly, the following precautions must be taken:

- Knead the skin with the right grade of humidity and at no high temperature in order to avoid the decrease of the break resistance.
- Avoid the use of organic solvents as they generally modify the chemical and physical characteristics of the product and the final use of organic solvents as they generally modify the
- For laminated leathers in particular, the use of adhesive and/or impregnating substances which contain solvents is not permitted as the lamina removing action of this type of substances has been verified even after a long time.
- Do not impregnate caps and / or counterforts with substances containing organic solvents, even if in traces, and let them dry as much as possible before their application.
- For varnished leather in particular, the organic solvents, which are eventually present in adhesives, impregnating substances, etc., can cause a detachment of the varnish film that would permanently compromise the aesthetic and functional characteristics of the products.
- Store the skins without overlapping any load on top of the packages provided by the tannery in order to avoid the formation of permanent creases.
- The micro-climatic conditions of the storage rooms must comply with the following optimal parameters: Relative Humidity 50/65% - Temperature 15/25 °C. In addition, it must ensure a good ventilation of the rooms.

However, it is not possible to foresee with absolute precision all the performances of the leather in its many different conditions of use. Therefore, it is good practice to test the leather by making prototypes according to the technological cycle established by the customer.

For the maintenance of the customer's products, take the following general precautions:

- Store them in dry and well-ventilated areas at room temperature.
- The use of products for the cleaning, protection and polishing of leather, generally has no side effects. Nevertheless, it is advisable to perform a preliminary test of the cleaning product on a hidden area of the customer's product.
- Warning: the use of products not specifically aimed at the maintenance of leather goods may cause cracks or colour fading on the treated surface.
- Stains caused by water-soluble substances (such as drinks, coffee, tea, milk, jam, etc.) can be removed from the surface by dabbing with absorbent paper without rubbing. Then, use a damp white cloth to gently treat the stain from the outside towards the inside and let the leather air dry. Finally, re-polish with a soft cloth. Stains caused by oily substances (such as oil, ketchup, mayonnaise, chocolate, etc.) can be removed with absorbent paper, by taking care not to press to prevent dirt from entering the skin. With a clean white cloth can be removed with absorbent solution, available at specific shops, gently rub from the outer to the inner part of the stain. Do not wet too much the skin surface and absorb any exceeding solution with a dry clean cloth. Let it air dry. The removal of both types of dirt must be carried out as quickly as possible.
- Warning: do not dry the skin in the sunlight or near heat sources!

The Quality Control wrote	Salvatore Daddio	
The Technical Manager confirm	Giampiero Russo	